



PILCHER HAMILTON CORPORATION

22PKN Premium Release Silicone Coated Film

MI-HOSTPH-22PKN-SIL-COAT-REL

Product Bulletin

Description

Hostaphan® 22PKN polyester film is silicone coated on one side. This special silicone coating is formulated to give premium release from selected solvent based adhesives. The other side is specially treated with a slip control coating to ensure proper tracking of the film web. Along with high strength, flexibility, and chemical resistance, this product provides excellent slip and good dimensional stability over a wide temperature range.


Performance

The silicone coating on Hostaphan® 22PKN is specially treated prior to winding. This silicone formulation provides premium release from certain solvent based adhesives. The special control slip coating treatment essentially eliminates the effect of backside silicone transfer. The slip controlled surface may act as a primed surface for printing using special polyester film inks.

FDA Status

Both sides of Hostaphan® 22PKN can be used for direct food contact applications subject to limitations found in 21 CFR 177.1630 and in accordance with good manufacturing practices. For more information, contact a Polyester Film Sales Representative.

Schematic of Hostaphan® 22PKN



Benefits

- Minimum silicone rub-off
- Provides very consistent release level with aging
- Excellent handling characteristics
- Clear distortion free coating
- Ultra-thin, highly cured coating which does not smear
- Better than 95% subsequent adhesion
- No static induced defects (Newton Rings)

WARNING:

Silicone coated film is very slippery. Do not discard scrap film on the floor. Injury may result if stepped on.

CAUTION

Backside control slip coating may interact with face stock top coats that are highly reactive, especially ones that are water sensitive or used in high humidity environments.

Abrasion of the backside control slip coating may result in the generation of small particulate contamination.

Typical Properties of Hostaphan® 22PKN Film

MI-HOSTPH-22PKN-SIL-COAT-REL

The Hostaphan® 22PKN property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Area Yield		in ² •mil/lb m ² •µm/kg	19,800 717	ASTM D 4321
Tensile Strength	MD	psi kg/cm ²	30,000 2,100	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm ²	15,000 1,050	ASTM D 882
Ultimate Elongation	MD	%	115	ASTM D 882
Modulus	MD	psi kg/cm ²	550,000 38,700	ASTM D 882
Coefficient of Friction A/B	Kinetic	—	0.20	ASTM D 1894
Shrinkage	MD TD	%	1.5 0.4	30 min. at 150°C
Density		g/cm ³	1.395	ASTM D 1505
Total Haze*		% 106 gauge 118 " 142 "	4.5 5.0 5.5	ASTM D 1003

SILICONE FUNCTIONALITY

Release From Silicone Side	g/in	<8	T-peel from Laminate
Release From Polyester Side		>300	@ 12 in./min

* Values for reference data only. Contact a Polyester Film Sales Representative for actual gauges available.

Approved TW 5/2009

PILCHER HAMILTON CORPORATION - 6845 KINGERY HIGHWAY WILLOWBROOK - IL 60527 - 630-655-8100 EXT. 107 - PILCHERHAMILTON.COM

Hostaphan is a registered trademark of Hoechst AG and is licensed

accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published **Pilcher Hamilton Corporation** specifications for one year following purchase, if properly handled, and except as required by law, **PILCHER HAMILTON CORPORATION** MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

©2000, 2008, 2021, 2022

. All rights reserved.