



PILCHER HAMILTON CORPORATION

3901
General Purpose Film
MI-HOSTPH-3901-CLR-GENPUR

Product Bulletin

Description

Hostaphan® 3901 is a clear polyester film, chemically treated on one side to reduce potential for scratching and improve handleability and roll quality. It combines high strength and durability, optical clarity, and excellent chemical resistance.


Performance

Hostaphan® 3901 provides a unique balance between clarity and handling characteristics. It can be metallized, printed and dyed. It is used in a wide variety of enduses, such as labels, copier belts, laminating, and drafting film.

Benefits

- Good handling characteristics
- Good clarity
- Reduced potential for scratching
- Good dimensional stability

Schematic of Hostaphan® 3901



Typical Properties of Hostaphan® 3901 Film

MI-HOSTPH-3901-CLR-GENPUR

The Hostaphan® 3901 property values below are typical measurements. Further guidance on series selection, functional behavior by end use, film processing, standard roll configuration and gauges is available through a Polyester Film Sales Representative.

Property		Unit of Measure	Typical Value	Test Method
Area Yield		in ² •mil/lb m ² •µm/kg	19,800 717	ASTM D 4321
Tensile Strength	MD	psi kg/cm ²	30,000 2110	ASTM D 882
Yield Strength (F5)	MD	psi kg/cm ²	15,000 1050	ASTM D 882
Ultimate Elongation	MD	%	150	ASTM D 882
Modulus	MD	psi kg/cm ²	500,000 35,200	ASTM D 882
Coefficient of Friction (A/B)	Kinetic	--	0.40	ASTM D 1894
Shrinkage	MD TD	%	1.2 0.4	30 min. at 150°C
Density		g/cm ³	1.395	ASTM D 1505
Total Haze*		%	200 gauge 2.1 300 " 2.5 400 " 2.9 500 " 3.3	ASTM D-1003

* Values for reference data only. Contact a Polyester Film Sales Representative for actual gauges available.

Approved RC 5/2016

PILCHER HAMILTON CORPORATION - 6845 KINGERY HIGHWAY WILLOWBROOK - IL 60527 - 630-655-8100 EXT. 107 - PILCHERHAMILTON.COM

Hostaphan is a registered trademark of Hoechst AG and is licensed

accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Pilcher Hamilton Corporation specifications for one year following purchase, if properly handled, and except as required by law, PILCHER HAMILTON CORPORATION, MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be non-conforming during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.

The information contained herein is believed to be true and